

TABOREN-PM 73 T 20-044



Description

TABOREN-PM 73 T 20-044 is a compound based on mixture of polypropylene block copolymer and polypropylene homopolymer filled with 20% of talc, stabilized with an UV additive package. It is designed for injection moulding technology and used in many industrial fields with stress put on excellent processability and good surface performance.

The grade is available in black colour.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

	Properties	Test method	Unit	Typical value
Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	13,0
	Density	ISO 1183-1	g/cm ³	1,04
Mechanical	Tensile Strength at Yield	ISO 527	MPa	25
	Charpy Notched Impact Strenght	ISO 179-1/1eA 23°C	KJ/m ²	4,5
	Charpy Unnotched Impact Strenght	ISO 179-1/1eU 23°C	KJ/m ²	35
	Elongation at Break	ISO 527	%	5
	Flexural Modulus	ISO 178	MPa	2700
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	150

Notes* The above values are typical for this material, not standardized.

TABOREN-PM 73 T 20-044

Processing Guidelines

Drying

TABOREN-PM 73 T 20-044 is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN-PM 73 T 20-044 can be processed without problems on standard moulding machines.

The following moulding parameters are to be used as guidelines:

Melt Temperature: 200 – 250°C
Injection Speed: Medium
Injection Pressure: 90 – 130 MPa
Hold-on Pressure: >40% of injection pressure
Mould Temperature: 30 - 50°C

Storage and handling

TABOREN-PM 73 T 20-044 should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation, colour changes and could have negative effects on the physical properties of the product.

Safety

TABOREN-PM 73 T 20-044 is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

Properties		Test method	Unit	Typical value
Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	13.0
	Density	ISO 1183-1	g/cm ³	1.04
Mechanical	Tensile Strength at Yield	ISO 527	MPa	25
	Charpy Notched Impact Strenght	ISO 179-1/1eA 23°C	KJ/m ²	4.5
	Charpy Unnotched Impact Strenght	ISO 179-1/1eU 23°C	KJ/m ²	35
	Elongation at Break	ISO 527	%	5
	Flexural Modulus	ISO 178	MPa	2700
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	150

Notes* The above values are typical for this material, not standardized.



AUTOMOTIVE APPLICATIONS



AUTOMOTIVE APPLICATIONS



AUTOMOTIVE APPLICATIONS



AUTOMOTIVE APPLICATIONS

AI
AF



CONSTRUCTION APPLICATIONS



CONSTRUCTION APPLICATIONS



CONSTRUCTION APPLICATIONS



HYGIENIC APPLICATIONS

CO
AF



GENERAL APPLICATIONS



GENERAL APPLICATIONS



GENERAL APPLICATIONS



CONSTRUCTION APPLICATIONS

AF



HYGIENIC APPLICATIONS



HYGIENIC APPLICATIONS



HYGIENIC APPLICATIONS



GENERAL APPLICATIONS

AP



UTOMOTIVE
PPLICATIONS



INSTRUCTION
PPLICATIONS



GENERAL
PPLICATIONS



HYGIENIC
PPLICATIONS