

# TABOREN-PR 73 T 10S-094

## Description

**TABOREN-PR 73 T 10S-094** is a compound based on mixture of polypropylene block copolymer and POE, filled with 10% of talc and stabilized with a basic antioxidant package. Additionally it contains an UV and anti-scratch additives. It is designed for injection moulding technology and used in many industrial fields with stress put on excellent processability and good surface performance. The grade is available in black colour.



**AUTOMOTIVE  
APPLICATIONS**



**CONSTRUCTION  
APPLICATIONS**



**GENERAL  
APPLICATIONS**



**HYGIENIC  
APPLICATIONS**

Properties		Test method	Unit	Typical value
Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	12,0
	Density	ISO 1183-1	g/cm <sup>3</sup>	0,960
Mechanical	Tensile Strength at Yield	ISO 527	MPa	15
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m <sup>2</sup>	60 P.B.
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m <sup>2</sup>	N.B.
	Elongation at Break	ISO 527	%	50
	Flexural Modulus	ISO 178	MPa	1100
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	121

**Notes\*** The above values are typical for this material, not standardized.

# TABOREN-PR 73 T 10S-094



## Processing Guidelines

### Drying

**TABOREN-PR 73 T 10S-094** is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

### Machine Requirements:

**TABOREN-PR 73 T 10S-094** is easy to process on standard injection moulding machines. The following moulding parameters are to be used as guidelines:

Melt Temperature:	200 - 250 °C
Injection Speed:	Medium
Injection Pressure:	90 - 130 MPa
Hold-on Pressure:	>40% of injection pressure
Mould Temperature:	30 - 50 °C

### Storage and handling

**TABOREN-PR 73 T 10S-094** should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation and colour changes a can have negative effects on the physical properties of the product.

### Safety

**TABOREN-PR 73 T 10S-094** is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety.

### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS





<b>Properties</b>	
<b>Physical</b>	Melt Flow Index (230°C / 2,16 kg)
	Density
<b>Mechanical</b>	Tensile Strength at Yield
	Charpy Notched Impact Strength
	Charpy Unnotched Impact Strength
	Elongation at Break
	Flexural Modulus
<b>Thermal</b>	VICAT Softening Temperature

**Notes\*** The above values are typical for this material, not st.

Test method	Unit	Typical value
ISO 1133	g/10 min	12.0
ISO 1183-1	g/cm <sup>3</sup>	0.960
ISO 527	MPa	15
ISO 179-1/1eA 23°C	KJ/m <sup>2</sup>	60 P.B.
ISO 179-1/1eU 23°C	KJ/m <sup>2</sup>	N.B.
ISO 527	%	50
ISO 178	MPa	1100
ISO 306 method A50	°C	121

andardized.