

TABOREN-PC 29 T 30-001



Description

TABOREN-PC 29 T 30-001 is a compound based on polypropylene block copolymer filled with 30% of talc, stabilized with an UV additive and high antioxidant content package. It is suitable for extrusion and blow moulding applications in many industrial fields with stress put on excellent processability and good surface performance. The grade is available in black colour.



**AUTOMOTIVE
APPLICATIONS**



**CONSTRUCTION
APPLICATIONS**



**GENERAL
APPLICATIONS**



**HYGIENIC
APPLICATIONS**

Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	0,9
	Density	ISO 1183-1	g/cm ³	1,13
Mechanical	Tensile Strength at Yield	ISO 527	MPa	24
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m ²	10
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m ²	45
	Elongation at Break	ISO 527	%	30
	Flexural Modulus	ISO 178	MPa	2700
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	148

Notes* The above values are typical for this material, not standardized.

TABOREN-PC 29 T 30-001



Processing Guidelines

Drying

TABOREN-PC 29 T 30-001 is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN-PC 29 T 30-001 can be processed without problems on all extrusion lines suitable for production of PP profiles and pipes.

Screw:

Abrasion protected coating of the screw is recommended due to the content of filler.

Length: 25D – 30D

Heating:

At least three separately controllable heating zones. The cylinder flange and adapter must be able to be heated.

Temperature Profile:

Hopper:	15 – 40°C
Zone 1:	180 – 190°C
Zone 2:	190 – 200°C
Zone 3:	200 – 210°C
Adapter:	200 – 210°C
Die:	200 – 210°C
Melt:	200 – 210°C



**AUTOMOTIVE
APPLICATIONS**



**CONSTRUCTION
APPLICATIONS**



**GENERAL
APPLICATIONS**



**HYGIENIC
APPLICATIONS**

TABOREN-PC 29 T 30-001



Storage and handling

TABOREN-PC 29 T 30-001 should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation, colour changes and could have negative effects on the physical properties of the product.

Safety

TABOREN-PC 29 T 30-001 is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety, recovery and disposal of the product or see our web pages www.silon.eu

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS