

TABOREN-PP 5001 GF



Description

TABOREN-PP 5001 GF is a compound based on polypropylene homopolymer filled with 20% of short glass fibres, stabilized with a basic antioxidant additive package. It is suitable for extrusion and blow moulding applications in many industrial fields with stress put on excellent processability and good surface performance. The grade is available in natural colour.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

	Properties	Test method	Unit	Typical value
Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	2,0
	Density	ISO 1183-1	g/cm ³	1,04
Mechanical	Tensile Strength at Yield	ISO 527	MPa	72
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m ²	9
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m ²	47
	Elongation at Break	ISO 527	%	5
	Flexural Modulus	ISO 178	MPa	4200
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	162

Notes* The above values are typical for this material, not standardized.

TABOREN-PP 5001 GF

Processing Guidelines

Drying

TABOREN-PP 5001 GF is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN-PP 5001 GF can be processed without problems on all extrusion lines suitable for production of PP profiles and pipes.

Screw:

Abrasion protected coating of the screw is recommended due to the content of glass.

Length: 25D – 30D

Heating:

At least three separately controllable heating zones. The cylinder flange and adapter must be able to be heated.

Temperature Profile:

Hopper:	15 – 40°C
Zone 1:	180 – 190°C
Zone 2:	190 – 200°C
Zone 3:	200 – 210°C
Adapter:	200 – 210°C
Die:	200 – 210°C
Melt:	200 – 210°C



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

TABOREN-PP 5001 GF



Storage and handling

TABOREN-PP 5001 GF should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation, colour changes and could have negative effects on the physical properties of the product.

Safety

TABOREN-PP 5001 GF is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety, recovery and disposal of the product or see our web pages www.silon.eu

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS