

# TABOREX TA 3004 HD

**A chemically-crosslinkable HDPE compound for the production of injection moulded fittings for domestic hot and cold water and central heating applications.**

## Description

**TABOREX TA 3004 HD** is a crosslinkable compound made of Silane grafted ethylene polymer. This graft polymer constitutes together with a TABOREX Masterbatch containing the crosslinking catalyst a "SIOPLAS-SYSTEM". Articles which are produced with the SILON grade TABOREX TA 3004 HD fulfil the requirements of ASTM F876, CSA 137.5, EN ISO 15875, BS 7291 and all related standards.

This system allows the compound to be handled as a normal thermoplastic polymer and will attain a high level of crosslinking in the processed form. The final product provides all the superior properties associated with crosslinked polyethylene.



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS

## Properties

	Properties	Test method	Unit	Typical value
Physical	Density	ISO 1183-1	g/cm <sup>3</sup>	0,954
	Melt Flow Index (190 °C/5 kg)	ISO 1133	g/10 min	6,5
	Bulk density	ISO 60	g/cm <sup>3</sup>	0,57
	Gel content	ISO 10147	%	> 68
	Volatile level	ČSN 640311	%	< 0,1
	Moisture (water)	ISO 15512	%	< 0,02
Mechanical	Tensile Strength at Break	ISO 527	MPa	27
	Elongation at Break	ISO 527	%	250

**Note:** the above values are typical for this material, not standardized.



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS

# TABOREX TA 3004 HD

## Processing Guidelines

### Extruder:

**TABOREX TA 3004 HD** can be processed on standard thermoplastic injections moulding machines without any problems. Particularly, in case the available screw is designed for Polyethylene, excellent products can be expected.

<b>Processing conditions:</b>	Melt Temperature	200 - 260 °C
	Mould Temperature	20 - 60 °C
	Screw Length	min. 15 d*
	* Screw diameter	

### Recommendation for optimal extrusion conditions:

- Pre-drying of foreign masterbatches e.g. colour, PPA and others. Drying has to be done preferably with dried air. Residual moisture of the added masterbatches must not exceed 0,02 %.
- Material preconditioning to ambient temperature before the package opening is necessary, to avoid moisture condensation on the pellet surface.
- Use screw suitable for PE-HD (3-zone or barrier screw).
- Head and tools should be designed allowing streamlined flow avoiding stagnation of the material.
- In case of line stop longer than 10–15 minutes: Before restarting purge with standard HDPE (MFI: 0,3 g/10 min.)



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS

# TABOREX TA 3004 HD

## Crosslinking Cure

The following methods are recommended:

- Autoclave using saturated steam at 100–115 °C (optimal method)
- By immersion in hot water at 80–95 °C
- Exposure to low pressure steam

The period required to obtain the final gel content depends on the wall thickness and the temperature. The exposure times are in the range of 4–8 hours.

## Storage and handling

**TABOREX TA 3004 HD** has a shelf life of nine months from the production date printed on the packaging. The packages should be stored in dry conditions at ambient temperature below 30 °C and protected from UV light. The packages should be opened only before processing and after opening of the inliner the product must be used within 3–4 hours.

## Packaging

Boxes of 600 kg containing a moisture resistant multilayer lining.



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS